

INTERNATIONAL STANDARD

**Materials for circuit boards and other interconnecting structures -
Part 3-6: Sectional specification set for unreinforced base materials clad and
unclad - Polytetrafluoroethylene (PTFE) filled laminate sheets of defined
flammability (vertical burning test), copper-clad**

CONTENTS

FOREWORD	3
1 Scope	5
2 Normative references	5
3 Terms, definitions and abbreviated terms	6
3.1 Terms and definitions	6
3.2 Abbreviated terms	6
4 Construction and materials	6
4.1 Construction	6
4.2 Resin system	6
4.3 Filler	6
4.4 Metal foil	6
4.5 Reinforcement	6
5 Internal marking	6
6 Electrical properties	6
7 Non-electrical properties of the base material	7
7.1 Appearance of the copper-clad sheet	7
7.1.1 General	7
7.1.2 Indentations (pits and dents)	7
7.1.3 Wrinkles	8
7.1.4 Scratches	8
7.1.5 Raised areas	8
7.2 Appearance of the unclad face	8
7.3 Laminate thickness	9
7.4 Bow and twist	9
7.5 Properties related to the copper foil bond	9
7.6 Heat shock	10
7.7 Machining	10
7.8 Dimensional stability	10
7.9 Sheet sizes and tolerances	11
7.9.1 Typical sheet sizes	11
7.9.2 Tolerances for sheet sizes	11
7.10 Cut panels sizes, tolerances and rectangularity	11
7.10.1 Cut panel sizes	11
7.10.2 Size tolerances for cut panels	11
7.10.3 Rectangularity of cut panels	11
8 Non-electrical properties of the base material after complete removal of the copper foil	12
8.1 General	12
8.2 Appearance of the dielectric base material	12
8.3 Flammability	12
8.4 Water absorption	13
8.5 Glass transition temperature and cure factor	13
8.6 Decomposition temperature	13
8.7 Z-axis CTE	13
8.8 X/Y-axis CTE	13
8.9 Thermal conductivity	14

9	Quality assurance	14
9.1	Quality system	14
9.2	Responsibility for inspection	14
9.3	Qualification inspection	14
9.3.1	General	14
9.3.2	Samples	14
9.3.3	Frequency	14
9.3.4	Criterion rule	14
9.4	Quality conformance inspection	15
9.4.1	General	15
9.4.2	Inspection lot	15
9.4.3	Group A inspection	15
9.4.4	Group B inspection	15
9.4.5	Group C inspection	16
9.4.6	Criterion rule	16
9.4.7	Rejected lots	16
9.5	Certificate of conformance	16
9.6	Safety data sheet	16
10	Packaging and marking	16
11	Ordering information	17
Annex A	(informative) Engineering information	18
A.1	General	18
A.2	Electrical properties	18
A.3	Non-electrical properties of the base material after complete removal of the copper foil	18
Bibliography	19
Table 1	– Electrical properties	7
Table 2	– Indentations	8
Table 3	– Nominal thickness and tolerance of metal-clad laminate	9
Table 4	– Bow and twist requirements	9
Table 5	– Peel strength requirements	10
Table 6	– Heat shock requirements	10
Table 7	– Dimensional stability	10
Table 8	– Size tolerances for cut panels	11
Table 9	– Rectangularity of cut panels	11
Table 10	– Flammability requirements	12
Table 11	– Water absorption requirements	13
Table 12	– Decomposition temperature requirements	13
Table 13	– Z-axis CTE requirements	13
Table 14	– X/Y-axis CTE requirements	13
Table 15	– Qualification and conformance inspection	14

INTERNATIONAL ELECTROTECHNICAL COMMISSION

**Materials for circuit boards and other interconnecting structures -
Part 3-6: Sectional specification set for unreinforced base materials clad
and unclad - Polytetrafluoroethylene (PTFE) filled laminate sheets of
defined flammability (vertical burning test), copper-clad**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) IEC draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). IEC takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, IEC had not received notice of (a) patent(s), which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at <https://patents.iec.ch>. IEC shall not be held responsible for identifying any or all such patent rights.

IEC 61249-3-6 has been prepared by IEC technical committee 91: Electronics assembly technology. It is an International Standard.

The text of this International Standard is based on the following documents:

Draft	Report on voting
91/2102/FDIS	91/2110/RVD

Full information on the voting for its approval can be found in the report on voting indicated in the above table.

The language used for the development of this International Standard is English.

This document was drafted in accordance with ISO/IEC Directives, Part 2, and developed in accordance with ISO/IEC Directives, Part 1 and ISO/IEC Directives, IEC Supplement, available at www.iec.ch/members_experts/refdocs. The main document types developed by IEC are described in greater detail at www.iec.ch/publications.

A list of all parts in the IEC 61249 series, published under the general title *Materials for circuit boards and other interconnecting structures*, can be found on the IEC website.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under webstore.iec.ch in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn, or
- revised.

1 Scope

This part of IEC 61249 specifies requirements for properties of polytetrafluoroethylene (PTFE) filled unreinforced laminated sheet of a thickness 0,02 mm up to 3,2 mm, of defined flammability (vertical burning test), copper-clad.

This document is applicable to the design, manufacture, use of PTFE filled unreinforced laminated sheet of defined flammability (vertical burning test), copper-clad.

Its flame resistance is defined in terms of the flammability requirements of 8.3.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 61189-2, *Test methods for electrical materials, printed boards and other interconnection structures and assemblies - Part 2: Test methods for materials for interconnection structures*

IEC 61189-2-721, *Test methods for electrical materials, printed board and other interconnection structures and assemblies - Part 2-721: Test methods for materials for interconnection structures - Measurement of relative permittivity and loss tangent for copper clad laminate at microwave frequency using split post dielectric resonator*

IEC 61189-2-803, *Test methods for electrical materials, printed board and other interconnection structures and assemblies - Part 2-803: Test methods for Z-axis expansion of base materials and printed boards*

IEC 61189-2-805, *Test methods for electrical materials, printed boards and other interconnection structures and assemblies - Part 2-805: X/Y CTE test for thin base materials by TMA*

IEC 61189-2-807, *Test methods for electrical materials, printed board and other interconnection structures and assemblies - Part 2-807: Test methods for materials for interconnection structures - Decomposition temperature (T_d) using TGA*

IEC 61249-5-1, *Materials for interconnection structures - Part 5: Sectional specification set for conductive foils and films with or without coatings - Section 1: Copper foils (for the manufacture of copper-clad base materials)*

ISO 11014, *Safety data sheet for chemical products - Content and order of sections*

IPC-TM-650 TM 2.5.5.5, *Stripline Test for Permittivity and Loss Tangent (Dielectric Constant and Dissipation Factor) at X-Band*

Bibliography

IEC 60194-1:2021, *Printed boards design, manufacture and assembly - Vocabulary - Part 1: Common usage in printed board and electronic assembly technologies*

IEC 60194-2:2025, *Electronic assembly, design and circuit boards - Vocabulary - Part 2: Common usage in electronic technologies as well as electronic assembly technologies*

IEC 60695-11-10, *Fire hazard testing - Part 11-10: Test flames - 50 W horizontal and vertical flame test methods*

ISO 9001:2015, *Quality management systems - Requirements*

ISO 14001:2015, *Environmental management systems - Requirements with guidance for use*

UL 94, *Standard for safety - Tests for Flammability of Plastic Materials for Parts in Devices and Appliances*
